



PRODUCT DATA SHEET

PROD. #2500 SERIES

POOL GUARD

CHLORINATED RUBBER SWIMMING POOL PAINT



PRODUCT DESCRIPTION

Richard's Pool Guard Chlorinated Rubber Swimming Pool Paint is a specially formulated coating designed to provide a rich and colorful finish for both interior and exterior new and old concrete pools. Its maintenance free finish is self priming, resists softening, chalking, chipping and peeling, and is suitable for fresh and salt water concrete ponds. Its chlorinated rubber formulation provides excellent durability offering years of service, while producing a tile-like smooth satin finish. It is easy to apply, resists scratching and marring, chemical actions of chlorine, and lime. It resists the growth of algae and fungus, is alkali attack, and resists extreme temperature fluctuations.

PRODUCT FEATURES	PRODUCT USES	PERFORMANCE QUALITIES	VOC COMPLIANCE																												
<ul style="list-style-type: none"> Chlorinated Rubber Superior Performance Self-Priming Resists Fading Alkali Resistant Algae & Fungus Resistant Chemical Resistant Excellent Coverage Easy To Apply 	<p>Suitable for the following properly prepared surfaces; INTERIOR / EXTERIOR</p> <table border="0"> <tr> <td>Concrete Pools</td> <td>Salt Water Pools</td> </tr> <tr> <td>Fresh Water Ponds</td> <td>Plaster Lined Pools</td> </tr> <tr> <td>Gunite Pools</td> <td>New & Old Pools</td> </tr> <tr> <td>Marcite Pools</td> <td>Masonry</td> </tr> <tr> <td>Water Fountains</td> <td>Stucco</td> </tr> </table> <p>Great For Both Interior & Exterior Pools!</p>	Concrete Pools	Salt Water Pools	Fresh Water Ponds	Plaster Lined Pools	Gunite Pools	New & Old Pools	Marcite Pools	Masonry	Water Fountains	Stucco	<p>Product Quality: Premium Best Product Use: Interior / Exterior Application: Brush, Roller & Airless Spray Product System: Solvent-Base Sheen: Satin</p>	<table border="0"> <tr> <td>AIM</td> <td>Yes</td> </tr> <tr> <td>OTC</td> <td>No</td> </tr> <tr> <td>CARB</td> <td>No</td> </tr> <tr> <td>SCAQMD</td> <td>No</td> </tr> <tr> <td>MPI #</td> <td>No</td> </tr> <tr> <td>LEED® 09CI</td> <td>No</td> </tr> <tr> <td>LEED® 09NC</td> <td>No</td> </tr> <tr> <td>LEED® 09CS</td> <td>No</td> </tr> <tr> <td>LEED® H</td> <td>No</td> </tr> </table>	AIM	Yes	OTC	No	CARB	No	SCAQMD	No	MPI #	No	LEED® 09CI	No	LEED® 09NC	No	LEED® 09CS	No	LEED® H	No
Concrete Pools	Salt Water Pools																														
Fresh Water Ponds	Plaster Lined Pools																														
Gunite Pools	New & Old Pools																														
Marcite Pools	Masonry																														
Water Fountains	Stucco																														
AIM	Yes																														
OTC	No																														
CARB	No																														
SCAQMD	No																														
MPI #	No																														
LEED® 09CI	No																														
LEED® 09NC	No																														
LEED® 09CS	No																														
LEED® H	No																														

SURFACE PREPARATION

General: Improper surface preparation is the direct cause of approximately 90% of all product failures in the application of pool paint coatings! Taking shortcuts will only cause problems. The entire surface area should be clean, dry, sound and free from all dirt, grease, oils, waxes, mildew, algae, fungus, loose mortar, loose scale, chalked, cracked and peeling paint, and any other surface contaminants that may cause paint failure.

- **Surface Repair:** Repair all holes, cracks and surface breaks with a grout or non-shrinking patching material specially made for concrete, marcite or gunite swimming pool repair. Allow all repairs to thoroughly dry before proceeding.
- **New/Unpainted Swimming Pools:** All new pools must be allowed a minimum of 60 days to properly age and cure. The pool should be properly etched with a solution of one (1) gallon of muriatic acid mixed with one (1) gallon of water, or any ready-mix cleaning and etching solution. Mix and apply in accordance with label directions. Rinse thoroughly with clean water and allow 24 hours to dry thoroughly. After rinsing the surface thoroughly, wash the surface once more with a strong solution of **Tri-Sodium Phosphate - (TSP)**, and warm water to effectively remove traces of acid and dirt, then rinse thoroughly with clean water and allow 24 - 48 hours to dry. This process should create a surface texture similar to that of 180 grit sandpaper, or this process must be repeated.
- **Previously Painted Swimming Pools:** Before performing any surface prep, test for the type of existing coating on the pool by wiping an inconspicuous surface area with denatured alcohol. If the existing coating **does not** soften, it is probably water-based, and **is not** suitable for re-coat with this product. Then test wipe the surface with Xylene, and if the surface **does** soften, it is probably chlorinated rubber and **is suitable** for re-coat with this product. Remove any loose scale, chalked, cracked or peeling coating from previously painted swimming pools by hand scraping, sanding, or power tool cleaning. Scrub the pool surface with a strong alkali detergent, such as TSP, using a stiff bristle brush to remove dirt, oils, or scum. Rinse thoroughly and allow to thoroughly dry. Sand the surface with 80 grit sandpaper to remove any gloss and to create an adequate profile for adhesion. If the existing coating is severely deteriorated, completely remove existing and treat as new. Repair any holes, cracks and surface breaks as stated above and allow to thoroughly dry. Once dry, acid etch the repaired areas using the methods described above.
- ❖ **Please refer to our Pool Guard Pool Paint Application Guide for more detailed Surface Preparation & Application Instructions.**
- **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how you can protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-Lead, or log onto www.epa.gov/lead.

PRODUCT ANALYSIS DATA

PIGMENT: 28.26%

VEHICLE: 71.74%

MORE DETAILED PRODUCT ANALYSIS DATA IS AVAILABLE UPON REQUEST.

TECHNICAL DATA

- **COLORS:** Pearl White & 4 Stock Colors
2505 Blue Lagoon 2510 Emerald Seas
2515 Sea Blue 2520 Black
- **TINTING:** Not Recommended
- **VEHICLE TYPE:** Chlorinated Rubber
- **VISCOSITY:** 63 KU ± 1
- **GLOSS @ 60°:** Satin / 25 Units ± 5
- **FLASH POINT:** 93° F
- **VOC:** Not to Exceed 600 g/l – 5.04 lb/gal
(Meets AIM SCAQMD Standards)
- **SOLIDS:** By Volume: 30.69% ± 2%
By Weight: 52.21% ± 2%
- **COVERAGE:** 300 – 400 Sq. Ft. / Gal.
(Coverage will vary significantly depending on application method, surface porosity and condition of the surface.)
- **MIL FILM:** Estimated @ 350 Sq. Ft. / Gal.
Wet: 4.6 mils **Dry:** 1.4 mils
- **DRY TIME:** (@ 70° F & 50% Relative Humidity)
To Touch: 30 – 45 Minutes
Recoat: Overnight
Full Cure: 7 Days
(Dry times listed may vary according to relative humidity, temperature, film build, color and air movement.)
- **CLEAN UP:** Xylene
- **THINNING:** Xylene

RECOMMENDED PRIMER COATINGS

Pool Guard is formulated to be self-priming on properly prepared new and painted pool surfaces.

- **New Concrete, Gunite & Marcite Pools:**
 - Self- Priming
- **Previously Painted Pool Surfaces:**
 - Self-Priming

APPLICATION EQUIPMENT

- **Brush Application:** Apply using quality nylon, polyester or combination nylon/polyester, or a quality natural china bristle brush.
- **Roller Application:** Apply using a 3/8" - 1 1/4" nap synthetic, lamb's wool or mohair roller cover, depending on texture or surface porosity.
- **Spray Application:**
 - **Pump:** Gas or Electric Airless Sprayer
 - **Pressure:** Minimum 2500 PSI
 - **Tip:** 0.015 – 0.019 Reversible
 - **Hose:** 1/4 inch (6.3 mm) - 3/8 inch (10 mm)

PACKAGING & WEIGHT PER GALLON

- **Packaging:**

Quarts – N/A	Gallons – 4/case
2 Gallons – N/A	5 Gallons – Each; (2500 & 2505 Only)
- **Weight per Gallon:** 10.51 lbs.

PRODUCT LIMITATIONS

- Not for use on Fiberglass Pool, Hot Tubs, Spas, Vinyl, Vinyl Lined, or Metal Swimming Pools.
- Not for use on pools previously painted with Epoxy or Waterborne Acrylic pool paints.
- Not for use in areas subject to intense heat.

CLEAN UP & THINNING INSTRUCTIONS

Clean Up: Clean up any minor spills and spatters immediately with **2500 TH Pool Paint Thinner**, as well as all painting tools and airless equipment. More serious paint spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

Thinning: Stir thoroughly and apply as it comes from the container. Thinning is not necessary. However, if thinning is required, you may thin the first coat **2500TH Pool Paint Thinner**.

WARRANTY & LIMITATIONS

The technical information contained herein is accurate to the best of our knowledge. All warranties are excluded, whether expressed or implied, by operation of law or otherwise, including all implied warranties of merchantability or fitness for a particular purpose. Seller shall not be liable, directly or indirectly, under any circumstances for consequential, incidental, special or any other type of damages arising or resulting for any reason under the sale, handling, or use of goods sold. Seller's liability hereunder, and buyer's exclusive remedy hereunder, for negligence or any other reason, is expressly limited to reimbursement of the purchase price of the materials sold after proof of purchase is provided to the seller. Notice of any alleged failure or defect in the material must be given to the seller in writing by certified U.S. mail within 15 days of noticing the problem. Failure to give the required notice within the time provided constitutes a waiver of any claim. The Manufacturer is not responsible for any misrepresentation made by the Dealer.

REV 07-14

PRODUCT APPLICATION – General

Richard's Pool Guard Chlorinated Rubber Swimming Pool Paint may be easily applied with a quality brush, roller cover, or airless spray equipment as follows;

- Stir thoroughly in a spiral up and down motion before and during application to keep product completely mixed.
- For best results, it is recommended to apply two (2) finish coats.
- To assure color uniformity always intermix multiple containers of custom tinted and stock colors. Apply a small test sample to verify color.
- On new surfaces, the first coat may be thinned with 2500TH Pool Paint Thinner to make a primer. Allow 24 hours to dry, then apply second coat un-thinned.
- When applying by brush, apply a smooth and generous coat on smaller surface areas, such as cutting-in larger surfaces and painting trim.
- When applying by roller, apply an even and generous coat in one direction avoiding any excessive re-spreading or reworking.
- Re-wet roller, then cross-roll previously applied coating.
- When applying by airless spray equipment, use a unit with a minimum of 2500 psi of pressure, with a 0.015 – 0.019 fluid spray tip.
- During spray application, it is recommended to back-roll the surface area to ensure proper adhesion, an even coat application and to work coating into surface pores.
- Maintain a wet edge during application by brushing, rolling or spraying into previously applied coating area.
- Apply when surface and ambient temperatures are above 55° F and below 90° F.
- Avoid paint application in direct sunlight by starting in the shaded area of the pool and follow the shade around the pool.
- Avoid exterior paint application when weather conditions are threatening, and late in the day when there is a threat of moisture condensing on wet paint.

PRECAUTIONARY & SAFETY INFORMATION

CAUTIONS: FLAMMABLE! CONTAINS XYLENE! KEEP OUT OF REACH OF CHILDREN! Keep away from heat, sparks and open flames. **INSURE PROPER CROSS-VENTILATION UNTIL COATING HAS DRIED!** Turn off main gas valve until after coating has dried, then have pilot lights relighted by a responsible person. Where ventilation is inadequate, use a suitable respirator. Avoid prolonged contact with skin and breathing of vapors and/or spray mists. When spraying this material, use an **OSHA** approved cartridge respirator. Use chemical safety glasses, goggles, or a face shield for proper eye protection. Wash thoroughly after handling and before eating or smoking. Close container after each use. **DO NOT TAKE INTERNALLY!**

FIRST AID: In case of skin contact, wash thoroughly with plenty of warm soapy water. For eye contact, flush with plenty of water for 15 minutes, **SEEK IMMEDIATE MEDICAL ATTENTION!** If affected by inhalation, move immediately to fresh air. If swallowed, **DO NOT INDUCE VOMITING, SEEK IMMEDIATE MEDICAL ATTENTION!**

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating the contents herein, may be harmful or fatal.

KEEP OUT OF REACH OF CHILDREN!